



## **RESOLUTION OIV-OENO 411-2011**

### **MONOGRAPH ON BIPOLAR ELECTRODIALYSIS MEMBRANES**

The GENERAL ASSEMBLY

In view of article 2, paragraph 2 iv of the Agreement of 3 April 2001, by which the International Organisation of Vine and Wine was founded,

CONSIDERING the work of the Group of Experts Technology concerning the use of bipolar electro dialysis membranes

CONSIDERING resolutions OIV-OENO 360/2010 and OIV-OENO 361/2010 adopted in 2010 concerning the acidification of wine and must by electromembranes (bipolar electro dialysis membranes)

Following a proposal made by the "Specifications of oenological products" experts group

HAS HEREBY DECIDED to add the following monograph to the international Oenological Codex:

### **MONOGRAPH ON BIPOLAR ELECTRODIALYSIS MEMBRANES**

#### **1. Object, origin and scope of application**

A bipolar membrane is a thin, dense, insoluble wall composed of a polymer material functionalized by ionic groups. A bipolar membrane has an anionic face and a cationic face; it is equivalent to combining a cationic membrane and an anionic membrane into a single membrane. Cationic and anionic membranes are defined in the International Oenological Codex (Electrodialysis membranes, Oeno 29/2000)

The membrane pair used in the bipolar electro dialysis acidification technique consists of a bipolar membrane and a cationic membrane. This arrangement, in the stack of an electro dialyser, only permits the extraction of cations..

- The cationic membrane allows the preferred flow of cations, in particular potassium.
- The function of the bipolar membrane is to maintain the acido-basic ionic balance of the system, following the extraction of a percentage of the potassium from the must or wine.

## **2. Composition of the membranes**

### **2.1. Composition of the cation membrane**

Cation membranes used in the acidification technique by bipolar membrane electro dialysis must comply with the prescriptions stated in the monograph concerning electro dialysis membranes (Oeno Resolution 29/2000) in the International Oenological Codex.

### **2.2. Composition of the bipolar membrane**

The bipolar membrane suitable for use is a styrene-divinylbenzene copolymer, whose cationic face and anionic face comply with the composition of cationic and anionic membranes described in the International Oenological Codex (Electro dialysis membranes, Oeno 29/2000)

### **2.3. They should be manufactured in accordance with the good manufacturing practices for the substances listed in:**

2.3.1. Annex 1 of the monograph on electro dialysis membranes (Resolution Oeno 29/2000) pertaining to materials placed in contact with foodstuffs.

2.3.2. Annexes 2 and 3 of the monograph on electro dialysis membranes (Resolution Oeno 29/2000) pertaining to ion-exchange resins used in processing foodstuffs.

### **2.4. They should be prepared to serve their intended function, in accordance with the instructions provided by the manufacturer or supplier.**

### **2.5. They should not release any substance in a quantity which endangers human health or which degrades the taste or odour of foodstuffs.**

### **2.6. In use, there should be no interaction between the constituents of the membrane and those of the must or wine likely to form new compounds in the treated product that could have toxicological consequences.**

## **3. Limits on use**

The diffusion of small molecules such as ethanol should be limited and should not



result in a reduction in the alcoholic strength greater than 0.1% by volume.

#### **4. Conditions of use**

The membranes shall be stored and cleaned using accepted techniques and substances whose use is authorised for the preparation of foodstuffs.